



US007267904B2

(12) **United States Patent**  
**Komatsu et al.**

(10) **Patent No.:** **US 7,267,904 B2**  
(45) **Date of Patent:** **Sep. 11, 2007**

(54) **NONAQUEOUS SECONDARY  
ELECTROLYTIC BATTERY**

(75) Inventors: **Shigeo Komatsu**, Kyoto (JP); **Hiroshi Mukai**, Kyoto (JP); **Tetsuya Murai**, Kyoto (JP); **Shinya Kitano**, Kyoto (JP); **Mikio Okada**, Kyoto (JP); **Hiroshi Nakahara**, Valencia, CA (US); **Mikito Nagata**, Valencia, CA (US); **Hiroyuki Yumoto**, Valencia, CA (US)

(73) Assignee: **GS Yuasa Corporation**, Kyoto (JP)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 586 days.

(21) Appl. No.: **10/712,530**

(22) Filed: **Nov. 14, 2003**  
(Under 37 CFR 1.47)

(65) **Prior Publication Data**

US 2004/0096735 A1 May 20, 2004

**Related U.S. Application Data**

(62) Division of application No. 09/582,868, filed as application No. PCT/JP99/06135 on Nov. 4, 1999, now Pat. No. 6,797,429.

(30) **Foreign Application Priority Data**

Nov. 6, 1998	(JP)	.....	P. 10-315967
Dec. 4, 1998	(JP)	.....	P. 10-344976
Mar. 29, 1999	(JP)	.....	P. 11-85155
Mar. 29, 1999	(JP)	.....	P. 11-85171
Mar. 29, 1999	(JP)	.....	P. 11-85208
Mar. 29, 1999	(JP)	.....	P. 11-85270
Mar. 29, 1999	(JP)	.....	P. 11-86977
Mar. 30, 1999	(JP)	.....	P. 11-88072
Mar. 30, 1999	(JP)	.....	P. 11-88251
Mar. 30, 1999	(JP)	.....	P. 11-88599

(51) **Int. Cl.**

**H01M 8/02** (2006.01)  
**H01M 2/08** (2006.01)

**H01M 2/02** (2006.01)

**H01M 2/00** (2006.01)

(52) **U.S. Cl.** ..... **429/176**; 429/185; 429/178;  
429/179; 429/171; 429/164; 429/163; 429/162;  
429/94

(58) **Field of Classification Search** ..... 429/176,  
429/185, 178, 179, 171, 164, 163, 162, 94  
See application file for complete search history.

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

4,092,464 A 5/1978 Dey et al.

(Continued)

**FOREIGN PATENT DOCUMENTS**

EP 0 862 227 A1 9/1998

**OTHER PUBLICATIONS**

Patent Abstracts of Japan: vol. 1997, No. 11, Nov. 18, 1997; JP 9-199099A, (Japan Storage Battery Co., Ltd.), Jul. 31, 1997.

*Primary Examiner*—Patrick Joseph Ryan

*Assistant Examiner*—Angela J. Martin

(74) *Attorney, Agent, or Firm*—Sughrue Mion, PLLC

(57) **ABSTRACT**

A nonaqueous secondary electrolytic battery comprising an electricity-generating element formed by spirally winding a laminate of a positive electrode plate, a separating material and a negative electrode plate, and an electrolytic solution with which the separating material, if it is a separator, is impregnated. The electricity-generating element is sealed in a battery case formed by a resin-laminated sheet comprising a metal layer as a barrier layer. Only a pair of lead terminals are drawn to the exterior of the battery case. The resin sheet comprises an oriented resin layer laminated on both surfaces of the metal layer. The inner heat-fused layers are opposed and heat-fused to each other. A molten and solidified resin mass is formed protruding from the inner end of the welded portion toward the inner space of the battery by 0.1 mm or more. Alternatively, the welded portion is formed thinner at the outer end thereof than at the inner end thereof.

**9 Claims, 19 Drawing Sheets**

